

# SEALMASTER PMCTS ULTRA PAVEMENT SEALER

*Factory Blended with Aggregate*

**SMT-152**

REVISED 08/02/18

## PRODUCT DESCRIPTION & BENEFITS

SealMaster PMCTS Ultra Pavement Sealer is a premium quality coal tar emulsion pavement sealer that is hot blended with cross-linking rubber polymers and special surfactants. PMCTS Ultra is applied at 48-55% solids as opposed to standard pavement sealers that are applied at 40-43% solids. PMCTS Ultra is factory blended with aggregate providing a safe skid-resistant surface for both pedestrian and vehicle traffic. PMCTS Ultra dries faster than conventional sealers due to the higher solids content.

## USES

SealMaster PMCTS Ultra is ideal for protecting and beautifying all types of pavement surfaces including parking lots, shopping malls, airports, driveways, roadways and more.

TABLE 1 - Physical Requirements of SealMaster PMCTS Ultra		
Property	Characteristics	
	Min	Max
Residue by Evaporation, %	48	-
Water Content, %	-	52
Aggregate Content, %	10	50
Ash Content of Residue, %	40	-
Solubility of Residue in CS <sub>2</sub> , %	20	-
Resistance to Volatilization, Residue Weight Loss, %	-	10
Drying Time, Firm Set, hours	-	8
Uniformity	No separation, coagulation, or settlement that cannot be overcome by moderate stirring - PASS	
Wet Film Continuity	Uniform homogenous consistency - PASS	
Resistance to Heat	No blistering, sagging or slipping - PASS	
Resistance to Kerosene	No loss of adhesion or penetration. No softening of the film - PASS	
Resistance to Water	No loss of adhesion and no blistering or tendency to re-emulsify - PASS	
Flexibility	No flaking, cracking, or loss of adhesion to the substrate - PASS	
P-625 Fuel Resistance Test	Evaluation of fuel resistance - PASS	
P-630 Fuel Resistance Test	Evaluation of fuel resistance - PASS	
P-631 Fuel Resistance Test	Evaluation of fuel resistance - PASS	

## ESTIMATING MATERIAL REQUIREMENTS

One gallon of SealMaster PMCTS Ultra will cover approximately 70 - 82 square feet per gallon per coat (7.75 - 9.1 square yards per gallon per coat).

## APPLICATION RATE

Apply PMCTS Ultra at a rate of 70 - 82 square feet per gallon per coat (7.75 - 9.1 square yards per gallon per coat). Application rates may vary due to pavement porosity and method of application.

## PERFORMANCE CHARACTERISTICS

SealMaster PMCTS Ultra consists of hot blended polymers and factory blended aggregate.

## SURFACE PREPARATIONS

Surface must be clean and free from loose material and dirt. Cracks should be filled with SealMaster Cold or Hot-Applied Crack Filling Materials. Oil stains should be cleaned and primed with SealMaster Oil Spot Primer.

## APPLICATION EQUIPMENT

SealMaster PMCTS Ultra shall be applied by mechanical squeegee/brush equipment or spray equipment capable of spraying coatings with sand. Equipment shall have continuous agitation or mixing capabilities to maintain homogeneous consistency of mixed material throughout the application process. Truck mount or self-propelled squeegee/brush equipment shall have at least 2 squeegee or brush devices (one behind the other) to assure adequate distribution and penetration of SealMaster PMCTS Ultra into bituminous pavement. Hand squeegees and brushes shall be acceptable in areas where practicality prohibits the use of mechanized equipment.

## MIXING PROCEDURES

Mix SealMaster PMCTS Ultra thoroughly before applying. If needed, a small amount of water may be added to facilitate application.

## APPLICATION PROCEDURES

For optimum performance and durability apply a minimum of two coats of SealMaster PMCTS Ultra. A third coat may be applied to high traffic areas such as parking lot entrances, exits and drive lanes for added durability. Allow each coat to dry thoroughly before applying successive coats. Allow final coat to dry for 24 hours prior to opening to vehicle traffic.

## APPLICATION WEATHER CONDITIONS

SealMaster PMCTS Ultra shall not be applied when temperature is expected to drop below 50° F during application and for a period of at least 24 hours after application. Do not apply if rain is imminent or forecast within 12 hours.

# SEALMASTER PMCTS ULTRA PAVEMENT SEALER

*Factory Blended with Aggregate*

**SMT-152**

REVISED 08/02/18

## **LINE STRIPING AND TRAFFIC MARKINGS**

Use SealMaster Traffic Paints for line striping and traffic markings.

## **PACKAGING AND AVAILABILITY**

SealMaster PMCTS Ultra is available for plant pick up or bulk tanker load quantities. SealMaster PMCTS Ultra is supported by a national network of SealMaster manufacturing and distribution facilities along with a national network of qualified applicators.

## **WARRANTY AND DISCLAIMER**

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose.

Copyright © InFrasys, Inc. All rights reserved. Reproduction of any of this material is strictly prohibited.



Phone: 1-800-395-7325

[www.sealmaster.net](http://www.sealmaster.net)