

ASPHALT BINDER

CMT-12

REVISED 12/19

PRODUCT DESCRIPTION & BENEFITS

SportMaster Asphalt Binder is an anionic asphalt emulsion.

USES

Apply to old oxidized asphalt track surfaces prior to the application of TrackMaster to achieve better coating adhesion.

COLOR

Available in Black.

Chemical Characteristics	
	% Weight (minimum)
Asphalt Emulsion (63.8% Non Volatile)	100

Product Data	
Type	Acrylic Emulsion
Pounds per gallon at 77°F	8.55 ± .5 lbs.
% Non Volatile Material	63.90 ± 3 lbs
Odor	Asphalt
Flammability	Non-Flammable
Flash Point	None
Storage Life	One Year
Colors	Black

SURFACE PREPARATION

Pavement surface must be cleaned entirely of dust, dirt, debris and all loose material.

MIXING PROCEDURES

Dilute 1 part Asphalt Binder with 5 parts water. Mix to a uniform consistency.

APPLICATION

Asphalt Binder can be brushed or sprayed onto surface.

IMPORTANT

Surface and air temperatures must be above 50°F (10°C) during application and for at least 24 hours after application. Stir before using. Do not apply when rain is imminent or forecast. Keep from freezing. Close container when not in use. Stir before using.

DRYING TIME

30 to 60 minutes under optimum drying conditions.

COVERAGE

.02 to .04 gallons per square yard. Yield calculations are based on undiluted gallons of Asphalt Binder.

CAUTIONS

Do not store in direct sunlight or where temperatures exceed 100°F. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use. Refer to product Safety Data Sheet (SDS) for additional safety information and precautions.

WARRANTY

The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or equipment furnished or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright © InFrasys, Inc. All rights reserved. Reproduction of any of this material is strictly prohibited.

ThorWorks Industries, Inc.
P.O. Box 2277
Sandusky, OH 44870

Phone: 1-800-326-1994
FAX: 1-419-626-5477
www.sportmaster.net