

# COLORPLUS PRO SYSTEM

**CMT-43**

REVISED 12/19

**PRODUCT DESCRIPTION & BENEFITS**

SportMaster ColorPlus Pro is a highly pigmented coating system designed for tennis courts and other sport and recreational pavement surfaces.

ColorPlus Pro features superior hiding, vibrance, and ultra-violet fade resistance.

**COLOR**

Forest Green, \*Light Green, Dark Green, Beige, Brown, \*Red, Maroon, Gray, Blue, Tournament Purple, Lt. Blue, \*Dove Gray, \*Ice Blue, and \*Sandstone

**LEED:** SS Credit 7.1:

Heat Island Effect: Non-Roof

\*Specific colors may contribute toward LEED credits.

**SURFACE PREPARATION**

Pavement surface must be cleaned entirely of dust, dirt, and debris. Repair of pavement surface defects, depressions and cracks must be completed prior to application. All repairs must be flush and smooth to adjoining surfaces.

New asphalt surfaces must cure 14 to 30 days prior to application. It is recommended that any uncoated asphalt surface receive one or more coats of Acrylic Resurfacer (Technical Bulletin CMT - 3) as required by surface roughness and porosity to provide a smooth, dense underlayment for application of color coatings.

New concrete surfaces must cure 28 days prior to application. Concrete surfaces should have a medium broom finish or similar roughened texture. Etch surface with muriatic or phosphoric acid and apply SportMaster Acrylic Adhesion Promoter (Technical Bulletin CMT - 21), prior to color coating.

**MIXING PROCEDURES**

Mix in the following order for 55 gallon drum of Neutral Concentrate:

- SportMaster Neutral Concentrate..... 55 gallons
- SportMaster ColorPlus ..... 8 gallons
- Water ..... 28-33 gallons
- Silica Sand ..... 400 lbs.  
(70 to 90 mesh AFS)

Mix in the following order for 30 gallon keg of Neutral Concentrate:

- SportMaster Neutral Concentrate..... 30 gallons
- SportMaster ColorPlus ..... 4 gallons
- Water ..... 15-18 gallons
- Silica Sand ..... 200 lbs.  
(70 to 90 mesh AFS)

**NOTE**

Mix thoroughly to ensure complete dispersion of ColorPlus.

**APPLICATION**

Apply mixed coating with a soft rubber squeegee. A minimum of two coats are recommended.

Product Data	
Type	Water Based Pigment Dispersion
Flammability	Non-Flammable
Flash Point	None
Colors	Several Available

**IMPORTANT**

Surface and air temperatures must be above 50°F (10°C) during application and for at least 24 hours after application. Stir before using. Do not apply when rain is imminent or forecast. Keep from freezing. Close container when not in use.

**CAUTIONS**

Do not store in direct sunlight or where temperatures exceed 100°F. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use. Refer to product Safety Data Sheet (SDS) for additional safety information and precautions.

**WARRANTY**

The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising,

## **COLORPLUS PRO SYSTEM**

**CMT-43**

**REVISED 12/19**

---

in connection with material or equipment furnished or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright © InFrasys, Inc. All rights reserved. Reproduction of any of this material is strictly prohibited.

ThorWorks Industries, Inc.  
P.O. Box 2277  
Sandusky, OH 44870

Phone: 1-800-326-1994  
FAX: 1-419-626-5477  
[www.sportmaster.net](http://www.sportmaster.net)