

## **SS-1H**SealMaster/Hawaii

**SMT-205** 

**REVISED 11/03/06** 

## **PRODUCT NAME**

SS1H SealMaster/Hawaii

## **CRUDE SOURCE**

Tesoro Hawaii Corporation #18168

## **MANUFACTURER**

SealMaster/Hawaii 2927 Mokumoa Street Honolulu, HI 96819-4044 Phone: (808) 839-2782 Fax: (808) 839-2002

www.sealmasterhawaii.com

Tank Number: 101 Sample Date: 9/30/06 Date Tested: 9/30/06 Sample ID#: 1002 Operator: LM

Method	Test	Specs Min/ Max	Result
T-59/D-244	Viscosity, SFS @ 77°F. s	20 / 100	23
T-59/D-244	Storage Stability, 24-h, %	/ 1.0	0.03
T-59/D-244	Cement Mixing, %	/ 2.0	0.9
T-59/D-244	Sieve, %	/ 0.10	0.03
T-59/D-244	Residue by Distillation, %	57 /	60.0
Tests On Residue From Distillation Test:			
T-49/D-5	Penetration, 77°F	40 / 90	56
T-5/D-113	Ductility, 77°F	40 /	89
T-44/D-2042	Solubility, %	97.5 /	99.5

These results relate only to the sample(s) tested.

This document shall not be reproduced except in full, without the approval of SealMaster Testing performed at the above location.

The above tests meet AASHTO M140 and ASTM D977 Requirements for Emulsified Asphalt.

Copyright @ InFrasys, Inc. All rights reserved. Reproduction of any of this material is strictly prohibited.

SealMaster/Hawaii Phone: (808) 839-2782 www.sealmasterhawaii.com