



CRACKMASTER 3405 HOT POUR CRACK SEALANT **SMT-191**

REVISED 6/5/18

PRODUCT DESCRIPTION

CrackMaster 3405 is a single component, hot applied crack and joint sealant. When melted and properly applied it forms a resilient crack sealant for both asphaltic and cementitious pavements. CrackMaster 3405 meets ASTM D3405, ASTM-D6690 Type I, II, and III, AASHTO-M301.

RECOMMENDED USES

CrackMaster 3405 is designed to seal expansion joints, longitudinal and transverse cracks, joints between concrete and asphalt shoulders, and random cracks in both asphalt and concrete pavements.

COMPOSITION

As supplied, CrackMaster 3405 is supplied in solid blocks comprised of asphaltic resins and synthetic polymer rubber.

SIZES

CrackMaster 3405 is supplied in 50 lb. cardboard cartons containing two 25 lb. blocks of material per carton.

COLOR

Black.

LIMITATIONS

Do not overheat material. Cracks must be free from moisture, dust, loose aggregate and other contaminants prior to application.

TECHNICAL DATA

CrackMaster 3405 meets the following material requirements when tested in accordance with ASTM D6690 Type I, II, & III, AASHTO M324, Type II, ASTM D3405, and SSS-1401C (see chart on right).

ENVIRONMENTAL CONSIDERATIONS

CrackMaster 3405 is considered a non-hazardous material.

INSTALLATION

Proper surface preparation will facilitate adequate adhesion and consequently the maximum service life of the sealant. The crack must be free from moisture, dust, and loose aggregate. Routing or wire brushing are preferred methods followed by a compressed air heat lance immediately prior to sealing. The substrate and air

temperature must be above 40°F.

METHODS


CrackMaster 3405 shall be melted in a conventional oiljacketed unit equipped with an agitator and temperature control device for both material and heat transfer oil. Carefully insert blocks of material (with plastic bag) into melting equipment with agitator turned off. Load material slowly to avoid splashing. After the initial load of material has reached the recommended pouring temperature (370-390°F), fresh material may be added as sealant is used. Melt only enough material that will be used the same day. Avoid overheating material. Excessive heat could cause material to gel in the equipment or fail in crack and joints. A significant viscosity increase accompanied by stringiness signals the approach of gelation. If this occurs, immediately remove the material from the melter and dispose of it.

IMPORTANT

Protective apparel is recommended with application of CrackMaster 3405. The extremely hot material will cause severe burns on contact with skin. OSHA Safety Regulations require workers to wear the following types of safety attire (see current OSHA/Safety Regulations for additional information): Hard hat with face shield; long sleeved shirt buttoned at the wrist; heat resistant gloves;

Geographical Performance of CrackMaster 3405

Pavement Temperatures (Fahrenheit)



Scale: ■ Recommended ■ Limited ■ Not Recommended

TABLE I - CHEMICAL & PHYSICAL ANALYSIS

Recommended Pour Temperature	370-390°F
Maximum Heating Temperature	410°F
Cone Penetration at 25°C	90 Max.
Resiliency	60% Min.
Flow at 140°F (5h)	3 mm Max.
Bond: -20°F/50% Ext	Passes 3 cycles
Bond: 0°F/100% Ext	Passes 3 cycles
Bond, water immersed	Passes 3 cycles at 50% ext. at -29°C
Specific Gravity	1.14
Asphalt Compatibility	Compatible
Viscosity	35 ± 20 poise

CRACKMASTER 3405 HOT POUR CRACK SEALANT

SMT-191

REVISED 6/5/18

long, cuffless pants; and safety toed work boots. Make certain all area around melter is clear of all debris and flammable materials. Avoid breathing vapors. Use with adequate ventilation.

MIXING PROCEDURES

Use material as supplied. Do not blend with other materials. After CrackMaster 3405 is melted it should be agitated or recirculated.

APPLICATION

Apply heated CrackMaster 3405 using either a pump and wand system or a pour pot. For best results the sealant depth to width ratio should not exceed 2 to 1 (i.e. 2-inches deep to 1-inch wide). The cooled sealant height should not exceed 1/8" above surrounding pavement. Using a sealing shoe or squeegee, band the material 2 to 3 inches wide over the crack.

ESTIMATING MATERIAL REQUIREMENTS

Use the following chart as a guideline for estimating material requirements (based upon pounds of material needed for 100 feet of cracks):

CRACK WIDTH	DEPTH	LBS/100 FT
3/8"	3/8"	6.9 lbs.
3/8"	1/2"	9.3 lbs.
1/2"	1/2"	12.3 lbs.
1/2"	1"	24.7 lbs.
3/4"	1/2"	18.5 lbs.
3/4"	3/4"	27.8 lbs.

The above coverage rates are only a guideline. Actual material usage may vary due to width of application and thickness of material above pavement surfaces.

PRECAUTIONS

Cracks must be free from moisture, dust, dirt, and debris. Both substrate and air temperature must be above 40°F. Keep boxes of material dry during storage. Do not store in direct sunlight.

WARRANTY AND DISCLAIMER

The statements made on this technical data sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement,

tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose.

Form No.: SMT-191

Revised: 6/18

Copyright © 2018, SealMaster
All rights reserved.



Phone: 1-800-395-7325

www.sealmaster.net