

1. PRODUCT NAME

SealMaster Coal Tar Ready-Mix Pavement Sealer

2. MANUFACTURER

SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone: 800-395-7325
www.sealmaster.net

3. PRODUCT DESCRIPTION & BENEFITS

SealMaster Coal Tar Ready-Mix Pavement Sealer is a pre-diluted clay-stabilized coal tar emulsion pavement sealer designed to protect and beautify asphalt pavement. Coal Tar Ready-Mix is formulated to be job-mixed with aggregate.

Basic Uses: SealMaster Coal Tar Ready-Mix is designed to beautify and protect asphalt pavement surfaces including parking lots, airports, driveways, shopping malls, roadways, and more.

Composition: SealMaster Coal Tar Ready-Mix is a pre-diluted clay-stabilized coal tar emulsion pavement sealer fortified with special surfactants to promote superior adhesion and durability. Select aggregate is job-mixed to produce a slip-resistant coating.

Sizes: SealMaster Coal Tar Ready-Mix is available in 4,000 gallon bulk tankers, 55-gallon drums, and 5-gallon pails.

Color: SealMaster Coal Tar Ready-Mix dries to a deep, rich black color.

Limitations: SealMaster Coal Tar Ready-Mix shall not be applied when temperature is expected to drop below 50°F at any time within a 24 hour period after application.

4. TECHNICAL DATA

SealMaster Coal Tar Ready-Mix meets the performance requirements of ASTM D 5727, RP 355e, ASTM D 490, FAA P627, FAA P628, P630, and P631 specifications for coal tar pitch emulsion (CTPE) pavement sealer.

Environmental Considerations: SealMaster Coal Tar Ready-Mix does not contain asbestos. Coal Tar Ready-Mix is an environmentally friendly water based pavement sealer containing less than 150 grams per liter volatile organic content (VOC).

Physical/Chemical Properties: SealMaster Coal Tar Ready-Mix is a premium quality pavement sealer that meets the following material requirements when tested in accordance with ASTM D 140, ASTM D 466, ASTM D 490, ASTM B117, ASTM D 529, ASTM D 2939, and ASTM D244 procedures. (see chart below)

5. INSTALLATION

Surface must be clean and free from all loose material and dirt. Pavement surface repairs should be made with a suitable hot or cold asphalt mix. Cracks should be filled with SealMaster hot pour or cold applied crack fillers. Treat all grease, oil, and gasoline spots or stains with SealMaster Petro Seal™ or Prep Seal™.

Methods: SealMaster Coal Tar Ready-Mix shall be applied by either pressurized spray application equipment or self-propelled

squeegee equipment. Pressurized spray equipment shall be capable of spraying pavement sealer with sand added. Equipment shall have continuous agitation or mixing capabilities to maintain homogeneous consistency of pavement sealer mixture throughout the application process. Self-propelled squeegee equipment shall have at least 2 squeegee or brush devices (one behind the other) to assure adequate distribution and penetration of sealer into bituminous pavement. Hand squeegees and brushes shall be acceptable in areas where practicality prohibits the use of mechanized equipment.

Mixing Procedures:

- For optimum results, SealMaster Coal Tar Ready-Mix Pavement Sealer shall be mixed in accordance with the following mix design (based on 100 gallons for ease of calculation):
Coal Tar Ready-Mix..... 100 gals.
Sealer V.M. Polymer
Additive..... 1-1.5 gals.
Sand*..... 200-400 lbs.
*(40-70 mesh AFS rating)

IMPORTANT: The above mix design

TEST	SPECIFICATIONS	RESULT
Material	Material shall be homogenous and show no separation or coagulation that cannot be overcome by moderate stirring.	PASSES
Chem. & Physical Analysis		
- Non Volatiles %	36% Minimum	PASSES
- Ash Non Volatiles %	30 - 40	PASSES
- Solubility of Non Volatiles in CS ₂	20 Min.	PASSES
- Specific Gravity 25°C	1.10 Minimum	PASSES
Drying Time	8 Hr. Max.	PASSES
Adhesion & Resistance to Water	No Penetration or Loss of Adhesion	PASSES
Resistance to Heat	No Blistering or Sagging	PASSES
Flexibility	No Cracking or Flaking	PASSES
Resistance to Impact	No Chipping, Flaking or Cracking	PASSES
Resistance to Volatilization	10% Loss in Weight Max.	PASSES
Wet Film Continuity	Smooth, Nongranular Free from Coarse Particles	PASSES

SealMaster® Coal Tar Ready-Mix Pavement Sealer

is a typical recommendation. Alternative mix designs may be substituted to account for local pavement conditions and use of other pavement sealer additives. However, in all cases sand shall be used in the mix design.

NOTE: Sealer V.M. is manufactured by SealMaster Industries, Inc. and is available from your local SealMaster facility.

Application: For optimum performance and durability apply two coats of properly mixed SealMaster Coal Tar Ready-Mix. A third coat of mixed Coal Tar Ready-Mix may be applied to high traffic areas such as entrances, exits, and drive lanes.

Application Rate of Mixed Coal Tar Ready-Mix: Apply properly mixed Coal Tar Ready-Mix (Coal Tar Ready-Mix, Sand, Additive) at a rate of .11 to .13 gallon per square yard (70-82 square feet per gallon) per coat.

Estimating Material Requirements: To estimate gallons of Coal Tar Ready-Mix required to cover a specific area use the following coverage rate:

- One gallon of Coal Tar Ready-Mix will cover approximately 80-95 square feet (8.9 to 10.5 square yards) per coat when properly mixed and applied.

Note: Coverage rates may vary due to pavement age and porosity.

Precautions: Both surface and ambient temperature shall be a minimum of 50°F. Temperature shall not drop below 50°F in a 24 hour period following application. New asphalt surfaces should be allowed to cure a minimum of four weeks under ideal weather conditions (70°F) before applying Coal Tar Ready-Mix. Keep Out Of Reach Of Children. Do not store unopened drums or pails in freezing temperatures.

6. AVAILABILITY & COST

Availability: SealMaster Coal Tar Ready-Mix is supported by a nationwide network of SealMaster manufacturing facilities along with a national network of professional applicators.

Cost: Cost information can be obtained from a local SealMaster Coal Tar Ready-Mix applicator. Contact SealMaster for the Coal Tar Ready-Mix representative in your area.

7. WARRANTY

SealMaster warrants that SealMaster Coal Tar Ready-Mix meets the chemical composition and performance requirements set forth in section 4. Liability to the buyer or user of this product is limited to the replacement value of the product only.

8. MAINTENANCE

Periodic cleaning of parking lot surface will ensure optimum product service life.

9. TECHNICAL SERVICES

Manufacturer: Complete product specifications, material safety data sheets, and technical assistance is available from SealMaster.

Professional Applicators: Your local SealMaster Coal Tar Ready-Mix applicator is available to provide on-site inspections and recommendations to meet your specific needs.

10. FILING SYSTEMS

- Sweet's Catalog
- Sweet's CD
- Sweet's Online
- Sweet's Directory
- SealMaster Online Specification at www.sealmaster.net
- Complete SealMaster Product and Equipment Catalog Available

The statements made on this specification sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose. Warranty is void on multi-coat applications if material made by other manufacturers is used with this product.

Form No.: SMT- 101

Revised: 1/14

Supersedes: SMT-101 (5/05), (12/09)

Copyright © 2014, SealMaster
All Rights Reserved.

SealMaster
Phone: 1-800-395-7325

www.sealmaster.net

SealMaster®

Pavement Products & Equipment