

**SS-1H**  
*SealMaster/Hawaii*

**SMT-205**

REVISED 11/03/06

**PRODUCT NAME**

SS1H  
 SealMaster/Hawaii

**CRUDE SOURCE**

Tesoro Hawaii Corporation  
 #18168

**MANUFACTURER**

SealMaster/Hawaii  
 2927 Mokumoa Street  
 Honolulu, HI 96819-4044  
 Phone: (808) 839-2782  
 Fax: (808) 839-2002  
 www.sealmasterhawaii.com

Tank Number: 101  
 Sample Date: 9/30/06  
 Date Tested: 9/30/06  
 Sample ID#: 1002  
 Operator: LM

Method	Test	Specs Min/ Max	Result
T-59/D-244	Viscosity, SFS @ 77°F. s	20 / 100	23
T-59/D-244	Storage Stability, 24-h, %	... / 1.0	0.03
T-59/D-244	Cement Mixing, %	... / 2.0	0.9
T-59/D-244	Sieve, %	... / 0.10	0.03
T-59/D-244	Residue by Distillation, %	57 / ...	60.0
<b>Tests On Residue From Distillation Test:</b>			
T-49/D-5	Penetration, 77°F	40 / 90	56
T-5/D-113	Ductility, 77°F	40 / ...	89
T-44/D-2042	Solubility, %	97.5 / ...	99.5

These results relate only to the sample(s) tested.

This document shall not be reproduced except in full, without the approval of SealMaster Testing performed at the above location.

The above tests meet AASHTO M140 and ASTM D977 Requirements for Emulsified Asphalt.

Copyright © 2006, SealMaster  
 All Rights Reserved.

SealMaster/Hawaii  
 Phone: (808) 839-2782  
 www.sealmasterhawaii.com