

PRODUCT DESCRIPTION & BENEFITS

PickleMaster RTU is a specialized coating system designed for use on pickleball court surfaces. The coating is available in 8 standard colors and produced with a fine rounded aggregate blend to provide non-slip texture without excessive wear on the balls.

USES

PickleMaster is a specialized sport surface coating, engineered for the sport of pickleball.

COLOR

Available in Dark Green, Forest Green, Light Green, Red, Beige, Blue, Brown (Field Mixed), Gray, and Maroon.

Product Data	
Type	Acrylic
Odor	Slight Ammonia
Flammability	Non-Flammable
Flash Point	None
Colors	Several Available

SURFACE PREPARATION

Pavement surface must be cleaned entirely of dust, dirt, debris and all loose materials. Repair of pavement surface defects, depressions and cracks must be completed prior to application. All repairs must be flush and smooth to adjoining surfaces.

New asphalt surfaces must cure 14 to 30 days prior to application. It is recommended to apply Acrylic Resurfacer (Technical Bulletin CMT3) as required by surface roughness and porosity to provide a smooth, dense underlayment for application of color texture and finish coats.

New concrete surfaces must cure 28 days prior to application. Concrete surfaces should have a medium broom finish or similar roughened texture. They must never be steel trowelled. Etch surface with Muriatic or Phosphoric Acid and apply SportMaster Adhesion Promoter prior to color coating.

MIXING PROCEDURES

PickleMaster RTU is ready to use. Do not add water. Stir thoroughly prior to application. A power drill and paddle mixer are recommended.

APPLICATION

Apply PickleMaster RTU with a soft rubber squeegee.

OFFICIAL
SURFACE OF



Allow each coat to thoroughly dry before applying the next coat. Two coats are recommended.

IMPORTANT

Surface and air temperatures must be above 50°F (10°C) during application and for at least 24 hours after application. Stir before using. Do not apply when rain is imminent or forecast. Keep from freezing. Close container when not in use.

COVERAGE

Approximately .12 to .15 gallon per square yard per Coat (60-75 Square Feet per gallon, per coat).

DRYING TIME

PickleMaster RTU dries in 30 to 60 minutes under optimum drying conditions. Allow 48 hours before allowing foot traffic or play.

CAUTIONS

Do not store in direct sunlight or where temperatures exceed 100°F. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use. Refer to product Safety Data Sheet (SDS) for additional safety information and precautions.

WARRANTY

The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or equipment furnished or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are



CMT-62

REVISED 07/20

installed.

Copyright© 2020, SportMaster
All rights reserved.

ThorWorks Industries, Inc.
P.O. Box 2277
Sandusky, OH 44870

Phone: 1-800-326-1994
FAX: 1-419-626-5477
www.sportmaster.net