

1. PRODUCT NAME

FlexMaster Crack Sealant

2. MANUFACTURER

ThorWorks Industries, Inc.
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-395-7325
Fax: 419-626-5477
www.thorworks.com

Additional Plant Locations:
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit website at www.sealmaster.net to find the location near you.

3. PRODUCT DESCRIPTION & BENEFITS

FlexMaster Crack Sealant is a one component, polymer modified asphalt emulsion crack sealant. It is a cold-applied material that exhibits the elastomeric qualities of hot pour crack and joint sealants.

FlexMaster is a premium quality crack sealant that provides a protective barrier against moisture intrusion into pavement surfaces. FlexMaster exhibits outstanding low temperature flexibility. FlexMaster offers the performance of a hot pour crack sealant with the safety and convenience of a cold-applied material.

Basic Uses: FlexMaster Crack Sealant is designed for filling cracks up to 1/2" wide in asphalt pavement surfaces.

Composition: FlexMaster Crack Sealant is an elastomeric, one component, polymer-modified asphalt emulsion crack sealant. Select mineral fillers are added for cohesive strength.

Sizes: FlexMaster Crack Sealant is available in 1-gallon, 5-gallon, and 55-gallon containers.

Color: Dries black.

Limitations: FlexMaster Crack Sealant shall not be applied when temperature is expected to drop below 50°F at any time within a 24

hour period immediately following application.

4. TECHNICAL DATA

Environmental Considerations:
FlexMaster Crack Sealant is a non-hazardous environmentally friendly water-based crack sealant containing less than 150 grams per liter volatile organic content (VOC).

Physical/Chemical Properties:
FlexMaster Crack Sealant meets the following material requirements when tested in accordance with ASTM D140, ASTM D466, ASTM D529, ASTM D2939, ASTM D244, ASTM D5-97, ASMT D5249, ASTM D5329, ASTM D36-95, ASTM D113, ASTM D3583, and ASTM D3236. (see chart below)

5. INSTALLATION

Cracks must be cleaned of all dirt, debris, and vegetation prior to application of crack sealant.

Methods: FlexMaster Crack Sealant may be applied directly from container (one gallon jug with pour spout), pour pot, or suitable mechanized pumping equipment.

It is desirable to squeegee material flush to adjoining pavement surface.

Mixing Procedures:
Stir material thoroughly. FlexMaster Crack Sealant is a ready-to-use

material. Do not dilute.

Application:
Pour Crack Sealant into cracks and squeegee flush to adjoining pavement. Allow material to dry before opening to traffic.

Estimating Material Requirements:
Coverage is dependent upon depth and width of cracks. Typically, one gallon of FlexMaster Crack Sealant will fill approximately 75-150 feet of cracks.

Precautions:
Both surface and ambient temperature shall be a minimum of 50°F. Temperature shall not drop below 50°F within a 24 hour period following application. Keep Out Of Reach Of Children. Do not store unopened containers in freezing temperatures.

6. AVAILABILITY & COST

Availability: FlexMaster Crack Sealant is supported by a national network of SealMaster facilities along with a national network of professional applicators.

Cost: Cost information can be obtained from a local applicator. Contact SealMaster for the name of the applicator in your area.

Chemical & Physical Analysis

| | |
|-------------------------------------|------------------------------------|
| Penetration (150 gr/5 sec)..... | 50 - 80 |
| Resiliency..... | >50% |
| Flow at 140°F..... | <5 mm |
| Softening Point..... | >150°F |
| Ductility @ 77°F..... | >30 cm |
| Bond @ 20°F (1" Mandrel)..... | PASSES |
| Specific Gravity..... | 1.10 |
| Asphalt Compatibility..... | Compatible |
| Non-Volatiles (%)..... | 60% min |
| Ash (Non Volatiles)..... | 18% min |
| Drying Time..... | Dependent Upon Thickness |
| Adhesion & Resistance to Water..... | No Penetration or Loss of Adhesion |
| Resistance to Heat..... | No Blistering or Sagging |
| Flexibility..... | No Cracking or Flaking |
| Resistance to Impact..... | No Chipping, Flaking, or Cracking |

FlexMaster Crack Sealant

7. WARRANTY

SealMaster warrants that FlexMaster Crack Sealant meets the chemical composition and performance requirements set forth in section 4. Liability to the buyer or user of this product is limited to the replacement value of the product only.

9. TECHNICAL SERVICES

Manufacturer: Complete product specifications, material safety data sheets, and technical assistance is available from SealMaster.

Professional Applicators: Your local applicator is available to provide on-site inspections and recommendations to meet your specific needs.

10. FILING SYSTEMS

- SealMaster Online Specifications at www.sealmaster.net
- Complete SealMaster Product and Equipment Catalog Available
- Sweet's Catalog
- Sweet's CD
- Sweet's Online
- Sweet's Directory

The statements made on this specification sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose. Warranty is void on multi-coat applications if material made by other manufacturers is used with this product.

Form No.: SMT-201
Revised: 7/04
Supersedes: SMT-59 (9/99)

Copyright © 2004, SealMaster
All rights reserved.

ThorWorks Industries, Inc.
2520 South Campbell St.
Sandusky, OH 44870

Phone: 1-800-326-1994
FAX: 1-419-626-5477

www.sealmaster.net

SealMaster®

Pavement Products & Equipment