

1. PRODUCT NAME:

SS-1H
SealMaster®/Hawaii

2. CRUDE SOURCE:

Tesoro Hawaii Corporation
#18168

3. MANUFACTURER:

SealMaster®/Hawaii
2927 Mokumoa Street
Honolulu, HI 96819-4404
Phone: (808) 839-2782
Fax: (808) 839-2002
www.sealmasterhawaii.com

Tank Number: 101
Sample Date: 9/30/06
Date Tested: 9/30/06
Sample ID#: 1002
Operator: LM

METHOD	TEST	SPECS MIN/MAX	RESULT
T-59/D-244	Viscosity, SFS @ 77°F. s	20 / 100	23
T-59/D-244	Storage Stability, 24-h, %	... / 1.0	0.03
T-59/D-244	Cement Mixing, %	... / 2.0	.09
T-59/D-244	Sieve, %	... / 0.10	0.03
T-59/D-244	Residue by Distillation, %	57 / ...	60.0
TESTS ON RESIDUE FROM DISTILLATION TEST:			
T-49/D-5	Penetration, 77°F	40 / 90	56
T-5/D-113	Ductility, 77°F	40 / ...	89
T-44/D-2042	Solubility, %	97.5 / ...	99.5

These results relate only to the sample(s) tested.
This document shall not be reproduced except in full, without the approval of SealMaster
Testing performed at the above location.

The above tests meet AASHTO M140 and ASTM D977 Requirements for Emulsified Asphalt.

Copyright © 2006, SealMaster
All Rights Reserved.

SealMaster/Hawaii
Phone: (808) 839-2782
www.sealmasterhawaii.com

SS-1H
SealMaster®/Hawaii
SMT - 205

SealMaster/Hawaii
Date: 11/06