

## 1. PRODUCT NAME

Zetac Pavement  
Sealer Additive

## 2. MANUFACTURER

ThorWorks Industries, Inc.  
2520 S. Campbell St.  
Sandusky, OH 44870  
Phone: 800-395-7325  
Fax: 419-626-5477  
www.thorworks.com

*Additional Plant Locations:*  
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit website at www.sealmaster.net to find the location near you.

## 3. PRODUCT DESCRIPTION & BENEFITS

Zetac is a high performance pavement sealer additive that enhances the adhesion and water resistance of the dried sealer film.

*Basic Uses:* Zetac is designed to enhance the performance of both asphalt based and coal tar based emulsion pavement sealers.

*Composition:* Zetac is a blend of synthetic polyamine compounds designed to enhance the adhesion properties and water resistance of asphalt and coal tar based pavement sealers.

*Sizes:* Zetac is available in 55 gallon drums and 5 gallon pails.

*Limitations:* SealMaster pavement sealers fortified with Zetac shall not be applied when temperature is expected to drop below 50°F at any time within a 24 hour period after application.

## 4. TECHNICAL DATA

Zetac meets the following material requirements when tested in accordance with ASTM D 2929. (see chart)

## 5. INSTALLATION

Surface must be clean and free from all loose material and dirt. Pavement surface repairs should be made with a suitable hot or cold

asphalt mix. Cracks should be filled with SealMaster hot pour or cold applied crack fillers.

*Methods:* SealMaster pavement sealers fortified with Zetac shall be applied by either pressurized spray application equipment or self-propelled squeegee equipment. Pressurized spray equipment shall be capable of spraying pavement sealer with sand added. Equipment shall have continuous agitation or mixing capabilities to maintain homogeneous consistency of pavement sealer mixture throughout the application process. Self-propelled squeegee equipment shall have at least 2 squeegee or brush devices (one behind the other) to assure adequate distribution and penetration of sealer into bituminous pavement. Hand squeegees and brushes shall be acceptable in areas where practicality prohibits the use of mechanized equipment.

### Mixing Procedures:

With mixing tank agitator turning, add proper amount of water to pavement sealer concentrate. Following the addition of water, add 2% Zetac based upon pavement sealer concentrate (2 gallons of Zetac per 100 gallons of pavement sealer concentrate). When mix begins to thicken add

sand slowly. Agitate thoroughly before and slowly during sealer application. Dilute Zetac 1:1 with water before adding to sealer mix to reduce polymer shock and promote uniformed dispersion.

*Important:* Wear long sleeve shirts, rubber gloves, and anti-splash goggles when working with Zetac.

*Application:* For optimum performance and durability apply 2 coats of properly mixed SealMaster pavement sealer fortified with Zetac. A third coat may be applied to high traffic areas such as entrances, exits, and drive lanes.

*Application Rate:* Apply mixed pavement sealer fortified with Zetac at a rate of .11 to .13 gallon per square yard (70-82 square feet per gallon) per coat.

*Note:* Application rates may vary somewhat due to pavement age and porosity.

*Estimating Material Requirements:* A minimum of 2 gallons of Zetac for every 100 gallons of SealMaster pavement sealer concentrate.

*Precautions:* Both surface and ambient temperature shall be a minimum of 50°F. Temperature shall not drop below 50°F in a 24 hour period following application. New

TEST	SPECIFICATIONS	RESULT
Material	Material shall be homogenous and show no separation or coagulation that cannot be overcome by moderate stirring.	PASSES
Chem. & Physical Analysis		
- Classification	Synthetic Polyamine Blend	PASSES
- Non Volatiles %	14 - 16%	PASSES
- Ash Non Volatiles %	<1%	PASSES
- Specific Gravity 25°C	Approx. 1.0	PASSES
Wet Film Continuity	Smooth, Nongranular Free From Coarse Particles	PASSES

# Zetac™

## Pavement Sealer Additive

asphalt surfaces should be allowed to cure a minimum of four weeks under ideal weather conditions (70°F) before applying SealMaster pavement sealer fortified with Zetac. Keep Out Of Reach Of Children. Do not store unopened drums or pails in freezing temperatures.

### 6. AVAILABILITY & COST

*Availability:* Zetac is supported by a nationwide network of SealMaster manufacturing facilities along with a national network of qualified applicators.

*Cost:* Cost information can be obtained from a local SealMaster applicator. Contact SealMaster for the applicator in your area.

### 7. WARRANTY

SealMaster warrants that Zetac meets the chemical composition and performance requirements set forth in section 4. Liability to the buyer or user of this product is limited to the replacement value of the product only.

### 8. MAINTENANCE

Periodic pavement sweeping will ensure optimum product service life.

### 9. TECHNICAL SERVICES

*Manufacturer:* Complete product specifications, material safety data sheets, and technical assistance is available from SealMaster.

*Professional Applicators:* Your local SealMaster applicator is available to provide on-site inspections and recommendations to meet your specific needs.

### 10. FILING SYSTEMS

- Sweet's Catalog
  - Sweet's CD
  - Sweet's Online
  - Sweet's Directory
  - SealMaster Online
- Specification at  
[www.sealmaster.net](http://www.sealmaster.net)
- Complete SealMaster Product and Equipment Catalog Available

The statements made on this specification sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose. Warranty is void on multi-coat applications if material made by other manufacturers is used with this product.

Form No.: SMT-182

Revised: 7/04

Supersedes: SMT-50 (4/99), SMT-182 (7/01)

Copyright © 2004, SealMaster  
All rights reserved.

ThorWorks Industries, Inc.  
2520 South Campbell St.  
Sandusky, OH 44870

Phone: 1-800-326-1994

FAX: 1-419-626-5477

[www.sealmaster.net](http://www.sealmaster.net)

**SealMaster®**  
  
Pavement Products & Equipment