

1. PRODUCT NAME

SealMaster TTP-1952b
Traffic Paint

2. MANUFACTURER

ThorWorks Industries, Inc.
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-395-7325
Fax: 419-626-5477
www.thorworks.com

Additional Plant Locations:
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit website at www.sealmaster.net to find the location near you.

3. PRODUCT DESCRIPTION & BENEFITS

SealMaster TTP-1952b Traffic Paint meets federal specification TTP-1952b for acrylic waterborne traffic paint. TTP-1952b Traffic Paint provides bright, durable line markings on asphalt and concrete pavement surfaces. Environmentally friendly 100% acrylic water based formula provides outstanding performance and durability.

Basic Uses: Asphalt or concrete parking lots, roads, streets, factory floors, and other pavement surfaces. Designed for interior or exterior use.

Composition: SealMaster TTP-1952b Traffic Paint is comprised of 100% acrylic emulsion resins, specialty pigments, surfactants, and fillers.

Sizes: 55-gallon drums, 5-gallon pails, and 1-gallon pails.

Color: White, Yellow.

Limitations: SealMaster TTP-1952b Traffic Paint shall not be applied when temperature is expected to drop below 50°F at any time within a 24 hour period after application.

4. TECHNICAL DATA

Environmental Considerations: SealMaster TTP-1952b Traffic Paint is an environmentally friendly 100%

acrylic emulsion traffic paint containing less than 150 grams per liter volatile organic content (VOC).

Physical/Chemical Properties: SealMaster TTP-1952b Traffic Paint meets the federal requirements set forth in the TTP-1952b specifications. (see chart below)

5. INSTALLATION

Asphalt and concrete pavement surfaces shall be clean and free from all loose materials and dirt. New asphalt surfaces should cure sufficiently to be free of light oils on the surface (4 weeks). Allow freshly applied pavement sealer to cure for at least 24 hours prior to applying traffic paint.

Methods: Apply SealMaster TTP-1952b Traffic Paint with pressurized spray equipment, brush, or roller. Recommended spray tip size is .017" to .021".

Mixing Procedures: Stir well before using. Use as is. Do not dilute.

Application: Apply Traffic Paint at a rate of at least 15 mils wet thickness (325 feet of 4-inch line). Apply to properly cleaned pavement with pressurized spray equipment, brush, or roller.

Estimating Material Requirements: One gallon of SealMaster TTP-1952b Traffic Paint will provide 325 feet of 4-inch line at 15 mils wet thickness. **NOTE** - Coverage rates will vary due to pavement porosity and application thickness.

Precautions: Both surface and ambient temperature shall be a minimum of 50°F. Temperature shall not drop below 50°F within a 24 hour period following application. Keep Out Of Reach Of Children. Do not store unopened containers in freezing temperatures.

6. AVAILABILITY & COST

Availability: SealMaster TTP-1952b Traffic Paint is supported by a nationwide network of SealMaster manufacturing facilities along with a national network of professional applicators.

Cost: Cost information can be obtained from a local applicator. Contact SealMaster for the representative in your area.

7. WARRANTY

SealMaster warrants that SealMaster TTP-1952b Traffic Paint

Chemical & Physical Analysis

	White	Yellow
Weight Per Gallon.....	12.35 lbs/gal.	12.40 lbs./gal.
Volatile Organic Content (VOC)	<150 g/l	<150 g/l
Viscosity (KU)	70 - 110	70 - 110
Dry To No Pick-Up Time.....	<30 min.	<30 min.
Scrub Resistance	1,000 cycles min.	1,000 cycles min.
Degree of Bleeding98 min.	.98 min.
Directional Reflectance.....	>86%	>50%
Dry Opacity	>0.965	>0.965
Water Resistance, cycles	8 min.	8 min.
PH of Paint	9.6 min.	9.6 min.
Solids (by weight) %	64 - 66	64 - 66

TTP-1952b

Traffic Paint

meets the chemical composition and performance requirements set forth in section 4. Liability to the buyer or user of this product is limited to the replacement value of the product only.

8. TECHNICAL SERVICES

Manufacturer: Complete product specifications, material safety data sheets, and technical assistance is available from SealMaster.

Professional Applicators: Your local applicator is available to provide on-site inspections and recommendations to meet your specific needs.

9. FILING SYSTEMS

- SealMaster Online Specifications at www.sealmaster.net
- Complete SealMaster Product and Equipment Catalog Available
- Sweet's Catalog
- Sweet's CD
- Sweet's Online
- Sweet's Directory

The statements made on this specification sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workmanship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose. Warranty is void on multi-coat applications if material made by other manufacturers is used with this product.

Form No.: SMT-243
Revised: 2/14
Supersedes: SMT-243 (7/04), (11/12)

Copyright © 2014, SealMaster
All rights reserved.

ThorWorks Industries, Inc.
2520 South Campbell St.
Sandusky, OH 44870

Phone: 1-800-326-1994
FAX: 1-419-626-5477

www.sealmaster.net

SealMaster®

Pavement Products & Equipment